



**Worldwide Foam**  
A Jacobs & Thompson Company

**1422**

EPDM

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:

1806 Conant St.  
Elkhart, IN 46516

[www.worldwidefoam.com](http://www.worldwidefoam.com)

[Info@worldwidefoam.com](mailto:Info@worldwidefoam.com)

Ph: 574-968-8268

Fax: 574-970-0926



Item	Specs	Test Method
Grade	2A1	ASTM D 1056-07
Density (PCF) (kg/m <sup>3</sup> )	4.37 - 5.62 PCF 70 - 90 kg/m <sup>3</sup>	ASTM D1056
Compression Deflection (CFD) (psi) (kPa) @25%	2.18 psi 15 kPa	ASTM D1056
Hardness - Durometer Shore OO	25- 45	ASTM D 2240
25% Compression Set %	20	ASTM D 1056
Tensile Strength (psi)(kPa)	43.5 psi 300 kPa	ASTM D412
Elongation (%)	150	ASTM D412
Tear Strength (lb/in)(kN/m)	8.6 lb/in 1.5 kN/m	ASTM D624

The data on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.