



**Worldwide Foam**  
A Jacobs & Thompson Company

**5420**

EPDM

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:

1806 Conant St.  
Elkhart, IN 46516

www.worldwidefoam.com

[Info@worldwidefoam.com](mailto:Info@worldwidefoam.com)

Ph: 574-968-8268

Fax: 574-970-0926



Item	Specs		Test Method
Grade	2A1/RE41		ASTM D1056
Density (PCF) (kg/m <sup>3</sup> )	3.1 – 6.2 PCF 21.6 - 26.4 kg/m <sup>3</sup>		ISO 845-88 AS
Compression Deflection (CFD) (psi) (kPa) @25%	2.9 psi 20 kPa		ASTM D 1056/85
Shore Hardness OO (Durometer)	30– 40		ASTM D2240
Compression Set %			ASTM D395
Tensile Strength (psi)(kPa)	46 psi 320 kPa		ASTM D412
Elongation (%)	>150%		ASTM D412
Tear Strength Resistance (lb/in)	11		ASTM D624
Water Absorption by Weight %	<5		ASTM D1056
Accelerated Age Testing: 7 Days @ 158 °F Change in CFD	<5%		ASTM D1204
Service Temperature (°F)(°C)	°F	°C	ASTM 3575
Low	-40	-40	
High	194	90	
Flame Resistance	Pass		FMVSS-302-S4.3
<b>Industry and OEM Specifications:</b> Jacobs and Thompson Inc. certifies that the following product meets the required specifications;	FMVSS 302		

The data on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.