



## **XE-20**

### Extruded Crosslinked Polyethylene

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:

1806 Conant St.

Elkhart, IN 46516

[www.worldwidefoam.com](http://www.worldwidefoam.com)

[Info@worldwidefoam.com](mailto:Info@worldwidefoam.com)

Ph: 574-968-8268 Fax: 574-970-0926



PHYSICAL PROPERTIES		TEST METHOD	VALUES	USA UNITS	VALUES	METRIC UNITS
Density - Nominal		ASTM D3575	2	lb/ft <sup>3</sup>	32	kg/m <sup>3</sup>
Tensile Strength		ASTM D3575	36	psi	248	kPa
Tear Strength		ASTM D3575	10	lb/in	178	kg/m
Elongation		ASTM D3575	110	%	110	%
Firmness		ASTM D2240	22	Asker C	22	Asker C
Compressive Stress						
Compression Set	50% 24hr	ASTM D3575 Suffix B	<30	%	<30	%
Compression Strength	25%	ASTM D3575 Suffix D	7	psi	48	kPa
	50%		26		179	
Working Temperature Range		Internal Test	-40 to 225	°F	-40 to 107	°C
Water Absorption 7 Days		ASTM-D1667	0.012	Lbs./sq.ft		
Flammability		FMVSS302	Pass	Pass/Fail	3.24"/min	Burn Rate

For roll size and color availability, please see the color and sizing chart, or contact us at [info@worldwidefoam.com](mailto:info@worldwidefoam.com) or visit [www.worldwidefoam.com](http://www.worldwidefoam.com)

\*Testing done according to ASTM D3575 & ASTM C177 (thermal conductivity) standards.

The data represented on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.